

## Facial Tissue 品質規格表

Base Weight (g/m <sup>2</sup> )	12.5 +/-1.0	12.0 +/-1.0	13.5 +/-1.0
Bulk mm (10sheets)		0.700 ↑	1.000 ↑
白色度 (% GE)	86.0 ↑	86.0 ↑	86.0 ↑
螢光劑	None	None	None
吸水度 mm (1st.min)	19+/-7	19+/-7	19+/-7
柔軟性 gf/25mm(2ply)	10+/-6		15+/-10
MD 引張強度 gf/25mm(2ply)	350 ↑	350 ↑	350 ↑
CD 引張強度 gf/25mm(2ply)	100 ↑	100 ↑	100 ↑

## Toilet Tissue 品質規格表

Base Weight (g/m <sup>2</sup> )	16.0+/-1.0		
Bulk mm (10sheets)	0.950 ↑		
白色度 (% GE)	84.0 ↑		
破裂 gf/cm (10sheets)	800 ↑		
吸水度 mm (1st.min)	26+/-6		
MD 引張強度 gf/25mm(2ply)	360 ↑		
CD 引張強度 gf/25mm(2ply)	120 ↑		

## Hand Towel 品質規格表

Base Weight (g/m <sup>2</sup> )	43.0	44.0	
Bulk mm (10sheets)	1.200 ↑	1.250 ↑	
白色度 (% GE)	83.0 ↑	83.0 ↑	
螢光劑	None	None	
吸水度 mm (1st.min)	14 ↑	14 ↑	
MD 引張強度 gf/25mm(1ply)	2340 ↑	2400 ↑	
CD 引張強度 gf/25mm(1ply)	510 ↑	530 ↑	

## Paper Napkin 品質規格表

Base Weight (g/m <sup>2</sup> )	17.0+/-1.0	18.0+/-1.0	
白色度 (% GE)	84.0 ↑	83.0 ↑	
螢光劑	None	None	
吸水度 mm (1st.min)	14 ↑	14 ↑	
MD 引裂強度 gf/25mm(2ply)	50 ↑	50 ↑	
MD 引張強度 gf/25mm(2ply)	750 ↑	750 ↑	
CD 引張強度 gf/25mm(2ply)	300 ↑	300 ↑	

## Kitchin Towel 品質規格表

Base Weight (g/m <sup>2</sup> )	19.0+/-1.0	21.0+/-1.0	22.5+/-1.0
白色度 (% GE)	84.0 ↑	84.0 ↑	84.0 ↑
螢光劑	None	None	None
吸水度 mm (1st.min)	24+/-6	15 ↑	15 ↑
MD 引張強度 gf/25mm(2ply)	360 ↑	400 ↑	1200 ↑
CD 引張強度 gf/25mm(2ply)	200 ↑	220 ↑	400 ↑